Appendix: Drill Results

Table 1: Dark Star Composite Drill Results

HOLE-ID	From (m)	To (m)	Core Length (m)	Au (g/t)	CN Rec (%)	Au GXM	Oxide Domain	Including 1g/t Au COG	Including 2g/t Au COG
DS24-01	1.52	3.05	1.5	0.17	92.5	0.26	Oxide		
DS24-01	155.45	158.50	3.0	0.42	105.7	1.27	Oxide		
DS24-01	184.40	185.93	1.5	0.18	96.6	0.27	Oxide		
DS24-01	192.02	237.74	45.7	0.67	66.2	30.69	Oxide	12.19m @ 1.24g/t Au & 81.8% CN Rec 3.05m @ 1.29g/t Au & 32.9% CN Rec	1.52m @ 2.11g/t Au & 104.6% CN Rec
DS24-02	9.14	13.72	4.6	0.18	73.4	0.80	Oxide		
DS24-02	243.84	248.41	4.6	0.44	49.6	2.01	Oxide		
DS24-02	252.98	277.37	24.4	1.40	17.4	34.07	Sulphide	19.81m @ 1.56g/t Au & 16.7% CN Rec	7.62m @ 2.4g/t Au & 11.7% CN Rec
DS24-03	188.98	190.50	1.5	0.22	69.8	0.33	Oxide		
DS24-03	201.17	220.98	19.8	0.77	67.4	15.17	Oxide	7.62m @ 1.57g/t Au & 65.9% CN Rec	3.05m @ 2.28g/t Au & 66% CN Rec
DS24-03	220.98	242.32	21.3	0.86	14.3	18.41	Sulphide	1.52m @ 1.89g/t Au & 30.7% CN Rec 3.05m @ 1.2g/t Au & 3.8% CN Rec 1.52m @ 1.32g/t Au & 4.6% CN Rec	
DS24-03	248.41	265.18	16.8	3.65	11.6	61.22	Sulphide	16.76m @ 3.65g/t Au & 11.6% CN Rec	15.24m @ 3.91g/t Au & 11% CN Rec
DS24-03	265.18	278.89	13.7	1.82	51.5	24.99	Oxide	9.14m @ 2.54g/t Au & 58.5% CN Rec	9.14m @ 2.54g/t Au & 58.5% CN Rec
DS24-04	56.39	59.44	3.0	0.34	56.7	1.04	Oxide		
DS24-04	65.53	89.92	24.4	0.22	49.7	5.43	Oxide		
DS24-04	108.20	111.25	3.0	0.20	71.6	0.60	Oxide		
DS24-04	121.92	138.68	16.8	0.38	68.8	6.39	Oxide		
DS24-05	150.88	163.07	12.2	0.28	65.1	3.43	Oxide		
DS24-05	187.45	188.98	1.5	0.20	59.7	0.31	Oxide		
DS24-06	128.02	131.06	3.0	0.29	79.5	0.87	Oxide		
DS24-06	192.02	193.55	1.5	0.28	100.0	0.43	Oxide		
DS24-06	210.31	213.36	3.0	0.39	62.6	1.20	Oxide		

Criteria: Cut off grade Ox 0.17g/t Au & Sx 0.5g/t Au, minimum length 1.5m, maximum consecutive internal waste 6m
OX= Oxide, Au/AuCN ≥ 40%, SX= Sulphide, Au/AuCN < 40%. True width of intercepts is uncertain but estimated to range between 40-85% of core length.
*A null grade value was allocated to unsampled intervals resulting from poor or no recovery within the mineralization zone and adjacent to mineralized intervals.

Table 2: Pinion Composite Drill Results

HOLE-ID	From (m)	To (m)	Core Length (m)	Au (g/t)	CN Rec (%)	Au GXM	Oxide Domain	Including 1g/t Au COG	Including 2g/t Au COG
PC24-01	76.20	113.84	37.6	1.15	52.7	43.34	Oxide	9.6m @ 2.1g/t Au & 44.7% CN Rec 6.25m @ 2.49g/t Au & 70.9% CN Rec	3.96m @ 2.77g/t Au & 35.5% CN Rec 1.07m @ 5.94g/t Au & 89.5% CN Rec
PC24-01	128.63	173.28	44.7	0.77	54.2	34.43	Oxide	7.92m @ 2.17g/t Au & 52.3% CN Rec	3.2m @ 2.89g/t Au & 63.7% CN Rec
PR24-01	141.73	195.07	53.3	0.51	89.8	27.29	Oxide	4.57m @ 1.25g/t Au & 87.9% CN Rec 1.52m @ 1.2g/t Au & 88.6% CN Rec	
PR24-01	202.69	205.74	3.0	0.24	95.4	0.74	Oxide		
PR24-01	208.79	210.31	1.5	0.18	84.3	0.27	Oxide		
PR24-02	80.77	97.54	16.8	0.32	93.6	5.40	Oxide		
PR24-02	121.92	161.54	39.6	0.31	91.2	12.45	Oxide	1.52m @ 1.25g/t Au & 95% CN Rec	
PR24-02	167.64	169.16	1.5	0.17	92.5	0.26	Oxide		
PR24-02	187.45	192.02	4.6	0.38	92.8	1.75	Oxide		

Criteria: Cut off grade Ox 0.17g/t Au & Sx 0.5g/t Au, minimum length 1.5m, maximum consecutive internal waste 6m
OX= Oxide, Au/AuCN ≥ 40%, SX= Sulphide, Au/AuCN < 40%. True width of intercepts is uncertain but estimated to range between 40-85% of core length.
*A null grade value was allocated to unsampled intervals resulting from poor or no recovery within the mineralization zone and adjacent to mineralized intervals.

Table 3: South Railroad Drill Hole Collars

Hole number	Target	Hole type	Grid	Easting m	Northing m	Elevation m	az_utm	dip	Depth (m)
DS24-01	Dark Star	RC	NAD27 / UTM zone 11N	588210.1	4480032.13	1998.7	240.0	-75.0	304.8
DS24-02	Dark Star	RC	NAD27 / UTM zone 11N	588211.6	4480033.58	1998.8	310.0	-70.0	335.3
DS24-03	Dark Star	RC	NAD27 / UTM zone 11N	588212.3	4480031.52	1998.7	270.0	-80.0	330.7
DS24-04	Dark Star	RC	NAD27 / UTM zone 11N	588065.1	4479794.09	2002.4	270.0	-65.0	204.2
DS24-05	Dark Star	RC	NAD27 / UTM zone 11N	587965.5	4479725.91	2037.2	0.0	-90.0	213.4
DS24-06	Dark Star	RC	NAD27 / UTM zone 11N	587965.5	4479725.90	2037.2	240.0	-70.0	213.4
PC24-01	Pinion	DD	NAD27 / UTM zone 11N	585305.2	4478684.10	2100.3	0.0	-90.0	189.9
PR24-01	Pinion	RC	NAD27 / UTM zone 11N	585197.0	4478681.72	2087.4	325.0	-68.0	213.4
PR24-02	Pinion	RC	NAD27 / UTM zone 11N	585217.5	4478738.66	2099.9	0.0	-90.0	237.7