

## Appendix: Drill Results

**Table 1: Camino Rojo Sulphide Extension Composite Drill Results (Composites 2g/t AuEq cog)**

HOLE-ID	From (m)	To (m)	Core Length (m)	Estimated True Width (m)	Au g/t	Ag g/t	Zn %	Cu %	Pb %	AuEq g/t (Au+Ag+Cu+Pb+Zn)	AuEq GXM	Including 5.0g/t AuEq COG	Including 10g/t AuEq HG	Litho
CRSX24-25H	742.50	744.00	1.5	1.3	2.09	1.2	0.02	<0.005	<0.005	2.12	3.18			Indidura
CRSX24-25H	871.00	872.40	1.4	1.2	0.03	231.0	0.05	0.04	<0.005	2.79	3.91			Indidura
CRSX24-25H	927.70	928.80	1.1	1.0	1.78	13.2	3.70	0.11	0.03	3.90	4.29			Cuesta de Cura
CRSX24-25H	1026.45	1027.30	0.8	0.7	13.05	27.3	13.95	0.10	0.04	20.38	17.32	0.8m @ 20.38g/t AuEq (13.05g/t Au, 27.3g/t Ag, 0.1% Cu, 0.04% Pb, 13.95% Zn)	0.8m @ 20.38g/t AuEq (13.05g/t Au, 27.3g/t Ag, 0.1% Cu, 0.04% Pb, 13.95% Zn)	Cuesta de Cura
CRSX24-25H	1128.55	1130.00	1.5	1.3	0.62	34.2	0.04	0.78	<0.005	2.07	3.00			Cuesta de Cura
CRSX24-25H	1134.00	1135.50	1.5	1.3	6.33	19.4	0.04	0.50	<0.005	7.24	10.86	1.5m @ 7.24g/t AuEq (6.33g/t Au, 19.4g/t Ag, 0.5% Cu, <0.005% Pb, 426ppm Zn)		Cuesta de Cura
CRSX24-25H	1145.20	1147.20	2.0	1.8	2.86	1.6	0.40	0.02	0.02	3.11	6.23			La Peñã
CRSX24-25H	1212.15	1212.90	0.8	0.7	3.12	15.8	7.36	0.11	0.03	7.07	5.30			La Peñã
CRSX24-25H	1292.00	1293.50	1.5	1.3	2.20	4.8	<0.005	0.01	<0.005	2.28	3.41			Cupido
CRSX24-31	705.80	706.30	0.5	0.4	10.00	64.4	7.29	0.11	0.74	14.72	7.36		0.5m @ 14.72g/t AuEq (10g/t Au, 64.4g/t Ag, 0.1% Cu, 0.74% Pb, 7.29% Zn)	Indidura
CRSX24-31	712.50	713.20	0.7	0.5	25.90	60.2	1.52	0.06	1.21	27.84	19.49	0.7m @ 27.84g/t AuEq (25.9g/t Au, 60.2g/t Ag, 0.06% Cu, 1.21% Pb, 1.52% Zn)	0.7m @ 27.84g/t AuEq (25.9g/t Au, 60.2g/t Ag, 0.06% Cu, 1.21% Pb, 1.52% Zn)	Indidura
CRSX24-31	747.00	748.00	1.0	0.7	2.12	27.5	0.96	0.02	0.23	3.02	3.02			Indidura
CRSX24-31	779.00	779.80	0.8	0.6	5.86	17.1	0.55	0.03	0.37	6.50	5.20			Indidura
CRSX24-31	805.50	807.25	1.8	1.3	1.99	4.3	0.20	0.01	0.01	2.15	3.77			Indidura
CRSX24-31	827.10	831.95	4.9	4.3	4.54	6.6	2.08	0.03	0.01	5.68	27.56	4.9m @ 5.68g/t AuEq (4.54g/t Au, 6.6g/t Ag, 0.03% Cu, 0.01% Pb, 2.08% Zn)	0.5m @ 27.83g/t AuEq (24.6g/t Au, 15.3g/t Ag, 0.06% Cu, 0.01% Pb, 6.03% Zn)	827.1 - 827.5 Indidura 827.5 - 831.95 Cuesta de Cura
CRSX24-31	835.50	837.00	1.5	1.1	2.38	25.7	2.07	0.08	0.01	3.81	5.71			Cuesta de Cura
CRSX24-31	944.00	946.85	2.9	2.1	5.65	26.6	1.43	0.04	0.13	6.76	19.27	1.5m @ 10.59g/t AuEq (9.34g/t Au, 44.5g/t Ag, 0.06% Cu, 0.23% Pb, 1.16% Zn)	1.5m @ 10.59g/t AuEq (9.34g/t Au, 44.5g/t Ag, 0.06% Cu, 0.23% Pb, 1.16% Zn)	Cuesta de Cura
CRSX24-31	996.70	997.60	0.9	0.8	5.26	3.3	1.33	0.02	<0.005	5.97	5.38			Cuesta de Cura
CRSX24-31	1001.30	1005.20	3.9	3.4	1.83	8.3	2.23	0.17	0.01	3.24	12.64	0.6m @ 13.97g/t AuEq (7.75g/t Au, 4.8g/t Ag, 0.09% Cu, <0.005% Pb, 12.3% Zn)	0.6m @ 13.97g/t AuEq (7.75g/t Au, 4.8g/t Ag, 0.09% Cu, <0.005% Pb, 12.3% Zn)	Cuesta de Cura
CRSX24-31	1108.00	1108.50	0.5	0.4	26.80	20.7	12.20	0.11	0.03	33.20	16.60	0.5m @ 33.2g/t AuEq (26.8g/t Au, 20.7g/t Ag, 0.11% Cu, 0.03% Pb, 12.2% Zn)	0.5m @ 33.2g/t AuEq (26.8g/t Au, 20.7g/t Ag, 0.11% Cu, 0.03% Pb, 12.2% Zn)	La Peñã
CRSX24-35B	1000.00	1001.50	1.5	1.3	2.62	0.5	0.02	<0.005	<0.005	2.64	3.96			Cuesta de Cura
CRSX24-35B	1041.35	1048.10	6.8	4.9	1.63	18.5	1.20	0.06	0.03	2.53	17.06			Cuesta de Cura
CRSX24-35B	1053.05	1053.55	0.5	0.4	11.80	37.6	0.83	0.20	0.08	12.93	6.46		0.5m @ 12.93g/t AuEq (11.8g/t Au, 37.6g/t Ag, 0.2% Cu, 0.08% Pb, 0.82% Zn)	Cuesta de Cura
CRSX24-35B	1058.70	1059.20	0.5	0.4	6.10	41.1	1.72	0.31	0.04	7.84	3.92			Cuesta de Cura
CRSX24-36A	1051.40	1051.90	0.5	0.4	4.68	38.0	1.92	0.04	0.05	6.14	3.07			Cuesta de Cura
CRSX24-36A	1276.60	1283.15	6.6	5.1	1.01	63.5	0.09	1.59	<0.005	3.90	25.53	1.2m @ 12.06g/t AuEq (3.08g/t Au, 202g/t Ag, 4.95% Cu, <0.005% Pb, 0.16% Zn)	1.2m @ 12.06g/t AuEq (3.08g/t Au, 202g/t Ag, 4.95% Cu, <0.005% Pb, 0.16% Zn)	La Peñã
CRSX24-36A	1292.20	1296.85	4.6	3.6	1.89	44.7	0.39	0.38	0.23	3.18	14.78	1.2m @ 7.83g/t AuEq (4.94g/t Au, 119g/t Ag, 0.44% Cu, 0.84% Pb, 1.32% Zn)		La Peñã
CRSX24-36A	1303.75	1304.30	0.5	0.5	2.71	59.3	0.09	1.80	<0.005	5.83	3.21			La Peñã
CRSX24-36A	1478.80	1481.15	2.4	2.0	5.35	8.5	2.17	0.34	<0.005	6.96	16.35	0.5m @ 25.23g/t AuEq (22g/t Au, 15.1g/t Ag, 0.61% Cu, <0.005% Pb, 4.57% Zn)	0.5m @ 25.23g/t AuEq (22g/t Au, 15.1g/t Ag, 0.61% Cu, <0.005% Pb, 4.57% Zn)	Cupido
CRSX24-36C	1064.35	1064.85	0.5	0.4	8.70	309.0	7.27	0.18	4.43	17.61	8.80	0.5m @ 17.61g/t AuEq (8.7g/t Au, 309g/t Ag, 0.18% Cu, 4.43% Pb, 7.27% Zn)	0.5m @ 17.61g/t AuEq (8.7g/t Au, 309g/t Ag, 0.18% Cu, 4.43% Pb, 7.27% Zn)	Cuesta de Cura
CRSX24-36C	1213.20	1219.25	6.0	4.4	1.91	17.7	0.65	0.21	0.04	2.74	16.56	1.5m @ 6.02g/t AuEq (5.02g/t Au, 28.5g/t Ag, 0.22% Cu, 0.06% Pb, 0.74% Zn)		1213.2 - 1216.4 Cuesta de Cura

												1216.4 - 1219.25 La Peñata		
CRSX24-36C	1223.00	1227.00	4.0	3.6	0.93	20.8	0.03	0.63	<0.005	2.02	8.10		La Peñata	
CRSX24-36C	1256.85	1258.05	1.2	1.1	0.65	36.6	1.11	0.78	0.02	2.65	3.18		La Peñata	
CRSX24-36C	1303.60	1306.50	2.9	2.6	3.63	9.4	0.01	0.23	<0.005	4.05	11.76	1.4m @ 6.17g/t AuEq ( 6g/t Au, 3.9g/t Ag, 0.09% Cu, <0.005% Pb, 0.01% Zn)	La Peñata	
CRSX24-36C	1388.80	1389.35	0.5	0.4	5.41	3.6	0.03	0.21	0.01	5.75	3.16		Cupido	
CRSX24-36C	1437.70	1440.00	2.3	2.1	2.27	1.5	0.61	0.02	<0.005	2.61	6.00		Cupido	
CRSX24-36C	1444.70	1447.40	2.7	1.9	30.74	3.8	1.32	0.08	0.01	31.54	85.16	2.7m @ 31.54g/t AuEq ( 30.74g/t Au, 3.8g/t Ag, 0.08% Cu, 0.01% Pb, 1.32% Zn)	0.6m @ 10.43g/t AuEq ( 9.51g/t Au, 8.1g/t Ag, 0.2% Cu, <0.005% Pb, 1.14% Zn) 0.6m @ 143.41g/t AuEq ( 140.5g/t Au, 9.2g/t Ag, 0.16% Cu, 0.03% Pb, 5.24% Zn)	Cupido
CRSX24-37	825.00	826.50	1.5	1.2	1.92	1.8	0.14	0.02	<0.005	2.03	3.05		Indidura	
CRSX24-37	891.58	892.80	1.2	1.0	2.85	10.9	0.74	0.15	0.01	3.53	4.31		Cuesta de Cura	
CRSX24-37	927.55	928.55	1.0	0.9	5.49	63.8	3.06	0.12	0.13	7.94	7.94	1m @ 7.94g/t AuEq ( 5.49g/t Au, 63.8g/t Ag, 0.12% Cu, 0.13% Pb, 3.06% Zn)	Cuesta de Cura	
CRSX24-37	961.00	962.50	1.5	1.2	6.52	9.5	3.29	0.03	0.02	8.30	12.45	1.5m @ 8.3g/t AuEq ( 6.52g/t Au, 9.5g/t Ag, 0.03% Cu, 0.02% Pb, 3.29% Zn)	Cuesta de Cura	
CRSX24-37	981.00	982.50	1.5	1.2	1.29	16.3	1.31	0.01	0.03	2.15	3.23		Cuesta de Cura	
CRSX24-37	996.50	998.20	1.7	1.3	4.83	2.4	0.87	0.02	<0.005	5.31	9.02	1.7m @ 5.31g/t AuEq ( 4.83g/t Au, 2.4g/t Ag, 0.02% Cu, <0.005% Pb, 0.87% Zn)	Cuesta de Cura	
CRSX24-37	1024.90	1025.40	0.5	0.4	25.10	34.4	2.68	0.03	0.03	26.87	13.44	0.5m @ 26.87g/t AuEq ( 25.1g/t Au, 34.4g/t Ag, 0.03% Cu, 0.03% Pb, 2.68% Zn)	0.5m @ 26.87g/t AuEq ( 25.1g/t Au, 34.4g/t Ag, 0.03% Cu, 0.03% Pb, 2.68% Zn)	Cuesta de Cura
CRSX24-37	1034.15	1034.75	0.6	0.5	2.63	41.8	5.22	0.24	0.02	6.01	3.60		Cuesta de Cura	
CRSX24-37	1061.00	1062.50	1.5	1.2	2.37	3.3	0.03	<0.005	<0.005	2.43	3.64		Cuesta de Cura	
CRSX24-37	1075.80	1078.60	2.8	2.4	1.04	12.5	1.84	0.07	0.01	2.18	6.11		Cuesta de Cura	
CRSX24-37	1086.95	1087.60	0.6	0.6	24.30	5.9	7.17	0.08	0.01	28.00	18.20	0.6m @ 28g/t AuEq ( 24.3g/t Au, 5.9g/t Ag, 0.08% Cu, 0.01% Pb, 7.17% Zn)	0.6m @ 28g/t AuEq ( 24.3g/t Au, 5.9g/t Ag, 0.08% Cu, 0.01% Pb, 7.17% Zn)	Cuesta de Cura
CRSX24-37	1119.80	1121.40	1.6	1.2	0.40	2.9	4.23	0.03	<0.005	2.55	4.08		La Peñata	
CRSX24-37	1201.50	1203.00	1.5	1.2	8.96	13.0	0.02	0.03	0.01	9.16	13.75	1.5m @ 9.16g/t AuEq ( 8.96g/t Au, 13g/t Ag, 0.03% Cu, 0.01% Pb, 0.02% Zn)	La Peñata	
CRSX24-37	1271.95	1276.05	4.1	3.5	2.42	29.4	0.05	0.11	0.07	2.95	12.09	1.1m @ 7.51g/t AuEq ( 7.26g/t Au, 2.3g/t Ag, 0.16% Cu, 0.01% Pb, <0.005% Zn)	La Peñata	
CRSX24-37	1313.05	1314.00	1.0	0.7	0.27	2.9	11.85	0.11	<0.005	6.27	5.95		Cupido	
CRSX24-38A	890.20	892.00	1.8	1.6	2.28	10.0	0.68	0.02	0.03	2.76	4.97		Cuesta de Cura	
CRSX24-38A	899.35	902.55	3.2	2.3	3.42	22.9	2.46	0.05	0.05	4.98	15.93	1.2m @ 8.35g/t AuEq ( 5.93g/t Au, 24.4g/t Ag, 0.07% Cu, 0.04% Pb, 4.12% Zn)	Cuesta de Cura	
CRSX24-38A	949.35	950.00	0.6	0.6	14.60	18.9	8.98	0.13	0.03	19.41	12.62	0.6m @ 19.41g/t AuEq ( 14.6g/t Au, 18.9g/t Ag, 0.12% Cu, 0.03% Pb, 8.98% Zn)	0.6m @ 19.41g/t AuEq ( 14.6g/t Au, 18.9g/t Ag, 0.12% Cu, 0.03% Pb, 8.98% Zn)	Cuesta de Cura
CRSX24-38A	971.15	971.65	0.5	0.4	61.50	60.2	5.92	0.48	0.07	65.77	32.88	0.5m @ 65.77g/t AuEq ( 61.5g/t Au, 60.2g/t Ag, 0.48% Cu, 0.07% Pb, 5.92% Zn)	0.5m @ 65.77g/t AuEq ( 61.5g/t Au, 60.2g/t Ag, 0.48% Cu, 0.07% Pb, 5.92% Zn)	Cuesta de Cura
CRSX24-38A	1047.00	1047.65	0.7	0.5	5.47	9.8	0.01	0.08	<0.005	5.70	3.71		Cuesta de Cura	
CRSX24-38A	1132.65	1133.90	1.3	1.1	3.96	8.5	4.31	0.11	0.01	6.32	7.90		Cuesta de Cura	
CRSX24-38A	1158.05	1158.85	0.8	0.6	3.60	10.5	5.65	0.20	0.01	6.77	5.42		Cuesta de Cura	
CRSX24-38A	1165.80	1166.30	0.5	0.5	6.36	11.7	4.48	0.08	0.01	8.81	4.40		La Peñata	
CRSX24-38B	889.35	889.85	0.5	0.4	18.10	48.1	5.13	0.14	0.06	21.38	10.69	0.5m @ 21.38g/t AuEq ( 18.1g/t Au, 48.1g/t Ag, 0.14% Cu, 0.07% Pb, 5.13% Zn)	0.5m @ 21.38g/t AuEq ( 18.1g/t Au, 48.1g/t Ag, 0.14% Cu, 0.07% Pb, 5.13% Zn)	Cuesta de Cura
CRSX24-38B	903.70	904.20	0.5	0.4	12.20	46.8	9.77	0.09	0.09	17.69	8.85	0.5m @ 17.69g/t AuEq ( 12.2g/t Au, 46.8g/t Ag, 0.09% Cu, 0.09% Pb, 9.77% Zn)	0.5m @ 17.69g/t AuEq ( 12.2g/t Au, 46.8g/t Ag, 0.09% Cu, 0.09% Pb, 9.77% Zn)	Cuesta de Cura
CRSX24-38B	918.50	919.00	0.5	0.4	7.38	72.1	5.36	0.12	0.31	11.11	5.56		Breccia	
CRSX24-38B	930.05	930.55	0.5	0.4	5.98	33.8	2.35	0.02	0.50	7.73	3.86		Cuesta de Cura	

CRSX24-38B	951.90	952.40	0.5	0.4	13.50	22.9	0.99	0.08	0.28	14.45	7.22	0.5m @ 14.45g/t AuEq ( 13.5g/t Au, 22.9g/t Ag, 0.08% Cu, 0.28% Pb, 0.99% Zn)	Cuesta de Cura
CRSX24-38B	1110.80	1116.08	5.3	4.3	3.61	2.7	0.83	0.06	0.01	4.13	21.79	1m @ 17.3g/t AuEq ( 15.25g/t Au, 6.5g/t Ag, 0.11% Cu, 0.03% Pb, 3.71% Zn)	1110.8 - 1111.8 Breccia 1111.8 - 1113.6 FG Intrusives - hdb-bi-pl 1113.6 - 1114.73 Breccia 1114.73 - 1116.08 Cuesta de Cura
CRSX24-38B	1268.15	1268.65	0.5	0.4	4.93	38.3	1.12	0.07	0.04	6.02	3.01		Cupido
CRSX24-39	1103.89	1104.40	0.5	0.4	9.99	105.0	1.76	0.30	0.12	12.52	6.38	0.5m @ 12.52g/t AuEq ( 9.99g/t Au, 105g/t Ag, 0.3% Cu, 0.12% Pb, 1.76% Zn)	Cuesta de Cura
CRSX24-39	1133.40	1134.85	1.4	0.9	2.33	285.0	2.17	0.51	0.75	7.63	11.06	1.4m @ 7.63g/t AuEq ( 2.33g/t Au, 285g/t Ag, 0.51% Cu, 0.74% Pb, 2.17% Zn)	Cuesta de Cura
CRSX24-39	1191.35	1198.05	6.7	4.2	1.47	8.3	0.56	0.17	<0.005	2.06	13.82		Cuesta de Cura
CRSX24-39	1347.25	1349.45	2.2	1.0	8.99	192.0	0.70	0.36	0.28	12.14	26.70	1m @ 22.66g/t AuEq ( 19.35g/t Au, 159g/t Ag, 0.47% Cu, 0.23% Pb, 1.54% Zn)	Breccia
CRSX24-39	1576.40	1578.40	2.0	1.1	0.83	393.4	8.77	0.08	2.40	10.62	21.25	1.5m @ 12.92g/t AuEq ( 0.71g/t Au, 500g/t Ag, 0.1% Cu, 3.04% Pb, 10.65% Zn)	La Peñã
CRSX24-40	1235.00	1237.00	2.0	1.8	2.99	11.2	0.56	0.02	0.02	3.43	6.86		La Peñã
CRSX24-40	1240.30	1241.50	1.2	1.1	2.41	1.4	0.05	0.12	<0.005	2.61	3.14		La Peñã
CRSX24-40	1266.00	1267.50	1.5	1.1	3.52	19.7	0.03	0.01	0.03	3.79	5.69		FG Intrusives - hdb-bi-pl
CRSX24-40	1386.50	1391.40	4.9	3.8	1.89	3.9	0.05	0.13	<0.005	2.13	10.42		Cupido
CRSX24-40	1405.25	1406.55	1.3	1.0	0.88	33.5	0.06	1.34	<0.005	3.07	3.99		Cupido
CRSX24-40	1411.20	1426.15	15.0	11.6	0.93	24.7	0.06	0.91	<0.005	2.45	36.57	0.5m @ 10.17g/t AuEq ( 2.69g/t Au, 105g/t Ag, 4.67% Cu, <0.005% Pb, 0.15% Zn)	Cupido
CRSX24-40	1442.90	1447.30	4.4	3.4	1.21	12.6	0.03	0.84	<0.005	2.49	10.97		Cupido
CRSX24-40	1483.20	1485.85	2.6	2.1	1.48	19.6	0.05	0.74	<0.005	2.71	7.19		Cupido
CRSX24-40	1519.30	1521.00	1.7	1.3	1.53	26.2	0.06	0.96	<0.005	3.14	5.33		Cupido
CRSX24-40A	1140.75	1145.22	4.5	2.7	5.17	215.1	4.59	0.14	3.33	11.24	50.23	2.8m @ 17g/t AuEq ( 8.07g/t Au, 299.4g/t Ag, 0.13% Cu, 5.17% Pb, 7.16% Zn)	Cuesta de Cura
CRSX24-40A	1171.75	1174.50	2.8	1.7	2.99	268.5	6.77	0.16	4.29	11.11	30.55	1.5m @ 16.87g/t AuEq ( 4.26g/t Au, 373g/t Ag, 0.17% Cu, 7.23% Pb, 11.4% Zn)	Cuesta de Cura
CRSX24-40C	1084.20	1085.50	1.3	0.9	0.43	32.6	7.84	0.24	0.05	5.00	6.50		Cuesta de Cura
CRSX24-40C	1162.08	1164.50	2.4	1.7	0.82	12.7	1.13	0.38	<0.005	2.03	4.92		Cuesta de Cura
CRSX24-40C	1193.70	1194.40	0.7	0.6	4.21	30.5	0.92	0.03	0.79	5.32	3.73		La Peñã

Criteria: Cut off grade 2g/t AuEq, minimum length 1.5m, maximum consecutive internal waste 3m, if Au grade x length > 3 the composite will be added

Price Assumptions: Au = 1750usd oz, Ag = 21usd oz, Cu = 3.5usd lb, Zn = 1.2usd lb

Note: CRSX24-39 was drilled down plunge to test continuity of mineralized system.

**Table 2: Camino Rojo Sulphide Composite Drill Results (Composites 1g/t Au cog)**

HOLE-ID	From (m)	To (m)	Core Length (m)	Estimated True Width (m)	Au g/t	Ag g/t	Zn %	Cu %	Pb %	AuEq g/t (Au+Ag+Cu+Pb+Zn)	Au GXM	Including 2.0g/t Au COG	Including 10g/t Au HG	Litho
CRSX24-25H	662.40	666.50	4.1	3.2	11.88	18.3	0.11	0.03	0.04	12.17	48.72	4.1m @ 11.88g/t Au ( 18.3g/t Ag, 0.03% Cu, 0.04% Pb, 0.11% Zn)	0.8m @ 20.8g/t Au (17.1g/t Ag, 0.02% Cu, 0.03% Pb, 0.02% Zn) 0.6m @ 35g/t Au (30.8g/t Ag, <0.005% Cu, 0.04% Pb, 0.01% Zn)	Caracol
CRSX24-25H	683.50	686.50	3.0	2.3	1.47	3.4	0.43	0.01	0.04	1.67	4.40			Caracol
CRSX24-25H	698.50	700.00	1.5	1.2	1.39	2.0	0.10	0.01	<0.005	1.46	2.08			Caracol
CRSX24-35	452.30	453.80	1.5	1.1	3.73	10.1	<0.005	<0.005	<0.005	3.84	5.60	1.5m @ 3.73g/t Au (10.1g/t Ag, <0.005% Cu, <0.005% Pb, <0.005% Zn)		Caracol

CRSX24-35	527.50	532.00	4.5	3.2	1.25	69.0	0.66	0.01	0.43	2.34	5.64	1.5m @ 2.45g/t Au (198g/t Ag, 0.03% Cu, 1.25% Pb, 1.56% Zn)	Caracol	
CRSX24-35	548.50	551.50	3.0	2.1	3.00	53.1	0.89	0.01	0.39	3.98	8.99	3m @ 3.98g/t AuEq (53g/t Ag, 0.01% Cu, 0.39% Pb, 0.89% Zn)	Caracol	
CRSX24-35	568.50	571.50	3.0	2.1	1.34	27.4	0.82	0.01	0.28	1.99	4.01		Caracol	
CRSX24-35	579.00	580.50	1.5	1.1	1.77	39.3	0.80	0.02	0.37	2.58	2.65		Caracol	
CRSX24-35	604.50	606.00	1.5	1.1	2.86	71.2	1.23	0.01	1.04	4.32	4.29	1.5m @ 2.86g/t Au (71.2g/t Ag, 0.01% Cu, 1.03% Pb, 1.23% Zn)	Caracol	
CRSX24-36C	703.50	704.00	0.5	0.4	5.92	105. 0	0.03	0.05	0.04	7.12	2.96		Caracol	
CRSX24-37	561.50	566.00	4.5	3.6	3.12	5.6	0.27	0.01	0.04	3.29	14.03	1.5m @ 7.4g/t Au (3g/t Ag, <0.005% Cu, <0.005% Pb, 0.11% Zn)	Caracol	
CRSX24-37	576.00	577.50	1.5	1.2	9.31	95.7	1.31	0.05	1.69	11.27	13.97	1.5m @ 11.27g/t AuEq (95.7g/t Ag, 0.05% Cu, 1.69% Pb, 1.3% Zn)	Caracol	
CRSX24-37	591.50	681.60	90.1	71.7	2.28	9.8	0.25	0.01	0.07	2.51	205.52	40m @ 2.78g/t Au (11.7g/t Ag, 0.02% Cu, 0.12% Pb, 0.25% Zn) 6.6m @ 6.28g/t Au (19g/t Ag, 0.03% Cu, 0.15% Pb, 1.24% Zn) 1.5m @ 7.48g/t Au (6g/t Ag, 0.02% Cu, 0.04% Pb, 0.03% Zn) 4.5m @ 3.22g/t Au (35.9g/t Ag, 0.01% Cu, 0.09% Pb, 0.17% Zn)	1.5m @ 11.5g/t Au (53.8g/t Ag, 0.01% Cu, 0.14% Pb, 0.2% Zn) 0.7m @ 12.5g/t Au (43.5g/t Ag, 0.01% Cu, 0.1% Pb, 0.28% Zn) 1.5m @ 22.8g/t Au (19g/t Ag, 0.03% Cu, 0.01% Pb, 0.12% Zn) 1.1m @ 13.2g/t Au (20.7g/t Ag, 0.02% Cu, 0.05% Pb, 0.36% Zn)	591.5 - 678.4 Caracol 678.4 - 681.6 Indidura
CRSX24-38B	656.50	664.00	7.5	6.5	3.30	12.0	0.65	0.02	0.10	3.70	24.74	7.5m @ 3.7g/t AuEq ( 3.3g/t Au, 12g/t Ag, 0.02% Cu, 0.1% Pb, 0.65% Zn)	1.5m @ 12.37g/t AuEq ( 10.95g/t Au, 29.5g/t Ag, 0.05% Cu, 0.19% Pb, 2.83% Zn)	Caracol
CRSX24-38B	681.35	683.50	2.1	1.9	4.42	7.4	0.11	<0.00 5	0.09	4.57	9.51	0.9m @ 9.15g/t AuEq ( 9g/t Au, 9.3g/t Ag, <0.005% Cu, 0.1% Pb, 0.05% Zn)	Caracol	
CRSX24-38B	690.40	692.00	1.6	1.4	1.99	34.6	0.37	0.01	0.58	2.63	3.18		Caracol	
CRSX24-39	578.00	596.00	18.0	12.7	1.03	11.3	0.29	0.01	0.15	1.30	18.53	1.5m @ 4.12g/t Au (16.2g/t Ag, 0.02% Cu, 0.22% Pb, 0.84% Zn) 1.5m @ 2.31g/t Au (31.2g/t Ag, 0.01% Cu, 0.44% Pb, 0.56% Zn) 1.5m @ 2.17g/t Au (15g/t Ag, 0.01% Cu, 0.22% Pb, 0.24% Zn) 4.9m @ 9.68g/t Au (48.1g/t Ag, 0.04% Cu, 0.16% Pb, 0.61% Zn) 7m @ 2.68g/t Au (6.7g/t Ag, 0.02% Cu, 0.04% Pb, 0.23% Zn)		Caracol
CRSX24-39	605.00	642.50	37.5	26.3	2.21	11.9	0.24	0.01	0.07	2.46	82.83	3m @ 3.94g/t Au (14.9g/t Ag, 0.04% Cu, 0.07% Pb, 0.49% Zn) 8m @ 2.97g/t Au (8.1g/t Ag, 0.01% Cu, 0.09% Pb, 0.17% Zn) 0.9m @ 86.3g/t Au (161g/t Ag, 0.09% Cu, 0.06% Pb, 0.06% Zn)	1.9m @ 22.2g/t Au (107g/t Ag, 0.1% Cu, 0.25% Pb, 1.03% Zn)	605 - 606.6 Caracol 606.6 - 608.55 Breccia 608.55 - 642.5 Caracol
CRSX24-39	654.50	657.50	3.0	2.1	3.94	14.9	0.49	0.04	0.07	4.34	11.81		Caracol	
CRSX24-39	665.00	673.00	8.0	5.6	2.97	8.1	0.17	0.01	0.09	3.15	23.80		Caracol	
CRSX24-39	693.20	695.90	2.7	1.9	29.17	54.8	0.05	0.03	0.02	29.82	78.76		Caracol	
CRSX24-40	551.00	552.00	1.0	0.8	2.49	352. 0	1.08	0.01	0.72	6.79	2.49		Breccia	

Criteria: Cut off grade 1g/t Au, minimum length 1.5m, maximum consecutive internal waste 6m, if Au grade x length > 1.5 the composite will be added

Price Assumptions: Au = 1750usd oz, Ag = 21usd oz, Cu = 3.5usd lb, Zn = 1.2usd lb

**Table 2: Camino Rojo Sulphide Extension Drill Hole Collars**

HOLE-ID	Easting	Northing	Elevation	Azimuth	Dip	Depth (m)
CRSX24-25H	243501.5	2676087.5	1954.6	172.6	-72.73	1310.4
CRSX24-31	243665.5	2676153.9	1953.4	144.7	-77.00	1247.8
CRSX24-35	243402.0	2675997.3	1956.3	139.8	-78.00	650.0
CRSX24-35B	243402.0	2675997.3	1956.3	146.0	-65.90	1222.4
CRSX24-36A	243305.3	2676111.1	1957.9	181.4	-62.53	1561.1
CRSX24-36C	243305.3	2676111.1	1957.9	151.5	-67.52	1500.0
CRSX24-37	243682.3	2676269.9	1953.9	148.0	-70.00	1352.0
CRSX24-38A	243550.9	2676268.3	1956.0	159.9	-57.10	1251.0
CRSX24-38B	243550.9	2676268.3	1956.0	160.9	-65.30	1400.1
CRSX24-39	243796.8	2676271.4	1951.7	204.7	-61.52	1646.1
CRSX24-40	243283.1	2676079.3	1957.4	172.9	-66.00	1587.5
CRSX24-40A	243283.1	2676079.3	1957.4	145.7	-52.11	1320.0
CRSX24-40C	243283.1	2676079.3	1957.4	169.0	-60.00	1337.2